

Noelson Chemicals

www.noelson.com

Formulation Guideline Meddle-Oil Iron Oxide Red Alkyd Primer

Guideline:

Part A

Product Name	Suggested Amount %
Meddle-oil alkyd resin	23.91
White spirit	13.28
Noelson™ Zinc Phosphate ZP 409-1	7.92
Noelson™ Iron Oxide 130N	8.85
Noelson™ Barium Sulfate	6
Noelson™ Bentone SD-1 (Anti-setting agent)	0.5
Flash rust inhibitor	1.0

Part B

(Add incrementally while stirring)

Product Name	Suggested Amount %
Meddle-oil alkyd resin	19.41
Cobalt dryer (6%)	0.23
Calcium dryer (6%)	0.19
Zirconium dryer (12%)	0.35
Anti-skinning agent	0.3

Disclaimer:

The guideline is provided for informational purposes only.

Note: the data given in this sheet are based on test results believed to be representative of the product, but should not be interpreted as binding specifications.