

# Noelson Chemicals

www.noelson.com

## Formulation Guideline Inorganic Zinc Silicate Primer

### Guideline:

#### Part A

Product Name	Suggested Amount %
Hydrolysates of ethyl silicate	28.8
Drying agent	0.6
Sericite mica	2.6
Noelson™ Claytone HY/HT (Bentonite)	1.66
Suspension agent	0.9
Ethyl alcohol	3.44
Zinc dust	46.6
Noelson™ SFPP-800M/Compound Ferro- Titanium Powder Ace Shield Pigment L-B/L-C)	15.4

### Disclaimer:

The guideline is provided for informational purposes only.