

# Noelson Chemicals

www.noelson.com

## Formulation Guideline Epoxy Zinc Rich Coating

### Guideline:

#### Part A

Product Name	Suggested Amount %
Epoxy resin	23.0 (60% in Xylene)
Bentonite	1.0
Zinc dust	54.0 (325 mesh)
Noelson™ SFPP-800M	10.0
TiO <sub>2</sub>	NA
Sericite mica	2.0
Wollastonite	3.0
Mixed solvent	9.0

#### Part B

Product Name	Suggested Amount %
Epoxy resin hardener	100.0

A/B = 10:1 (by weight)

### Disclaimer:

The guideline is provided for informational purposes only.