

Noelson Chemicals

www.noelson.com

Formulation Guideline Air Dry Alkyd Anti-Corrosive Primer

Guideline:

Product Name	Suggested Amount %
Long-oil alkyd resin	40.0
Noelson™ 130N (Iron Oxide)	16.1
Noelson™ ZP 409-3 (Zinc Phosphate)	8.0
Talc filler	9.6
Noelson™ barium sulfate	4.3
Noelson™ ZnO	0.9
Dispersing agent	0.2
High boiling point solvent	2.0
Ethanol solvent	19.1
Cobalt dryer (6%)	0.6
Plumbum dryer (24%)	0.4
Anti-skinning agent	0.2

Disclaimer:

The guideline is provided for informational purposes only.

Note: the data given in this sheet are based on test results believed to be representative of the product, but should not be interpreted as binding specifications.