

Noelson Chemicals

www.noelson.com

Formulation Guideline PUR Steel Structure Coating

Guideline:

Part A

Product Name	Suggested Amount %
Hydroxylic acrylic resin (Bayer Desmophen A160)	31.85
Soft acrylic resin (BASF Acronal 700L)	0.51
Anti-setting agent (10% Bentone 38 in Xylene)	9.94
TiO ₂	9.2
Noelson™ Iron Oxide 130N	5.48
Talc filler	6.53

Part B

Product Name	Suggested Amount %
Noelson™ MIO AS (A-320M)	25.67
Solvent Oil #100	3.18

Part C

Product Name	Suggested Amount %
PU Hardener (Bayer Desmodur N75 MPA)	7.64

Disclaimer:

The guideline is provided for informational purposes only.

Note: the data given in this sheet are based on test results believed to be representative of the product, but should not be interpreted as binding specifications.